

Technical Data Sheet

ADSINT® PA11 FR

AdSint® PA11 FR has been specially developed for flame retardant applications. PA11 FR fulfils the flame protection classification UL 94 / V-0 from a wall thickness higher than or equal to 3.2 mm. It is halogen free. The end product offers high chemical resistance. Typical applications include electrical components where flame retardancy is a required. **AdSint® PA11 FR** has been tested on most common SLS printers. Parameters for printing will be provided. The refresh rate is 50%.

General properties

Measurement	Method & Conditions	Metric Value
Mean Diameter	ISO 13320	40 µm
Particle Size Distribution		
Fine Particles < 15 µm	ISO 13320	10 max. %
Coarse Particles > 76 µm		10 max. %
Bulk Packed Density 23°C	ISO 1068-1975	0,53± 0,05g/cm ³
Part Density 23°C	ISO 61	1.00± 0,05g/cm ³
Part Water absorption at 23°C, 50% RH at equilibrium	ISO 62/1	0.9 to 1.1%

Thermal properties

Measurement	Method & Conditions	Metric Value
Melting point T ^m	ISO 11357-3	201°C
Melting point T ^m (Sintered Part)	ISO 11357-3	190± 2°C
Glass transition temperature T ^g (Sintered Part)	ISO 11357-3	41±2°C
Heat Deflection Temperature (HDT @0.45MPa)	ISO 75f	150± 2°C
Heat Deflection Temperature (HDT @1.8MPa)	ISO 75f	44± 2°C
Flammability	UL 94	V-0 thickness ≥ 3.2mm

Mechanical properties

Measurement	Method & Conditions	Metric Value
Tensile strength	ISO 527-2:93-1B	33.5 ± 2 MPa
Tensile modulus	ISO 527-2:93-1B	1650 ± 50 MPa
Elongation at break	ISO 527-2:93-1B	15 ± 5 %
Flexural modulus	ISO 178 (23°C)	1610 ± 100 MPa
Charpy – Impact strength (unnotched)	ISO 179 1eU (23°C)	35 ± 15 kJ/m ²
Hardness (Shore D – instantaneous)	ISO 868 (20°C)	76±1

Handling – storage

Store the product in original packaging away from moisture and heat. Under these conditions, the material will maintain its technical properties for 3 years. Once the material passes the 3-year limit, it will be necessary to perform testing of the specified data to restart the shelf life period.

Delivery Form

The material will be delivered in 2kg bottles or 20kg drums (2x10kg powder bags).

The information presented in this document is provided in goodwill and represents the best of ADVANC3D Materials' knowledge about the product. It is purely informative. No warranty of fitness for any particular purpose, warranty of merchantability or any other warranty, expressed or implied, is made concerning the goods described or the information provided herein.